



Factory Address : W-60, Phase II, MIDC, Dombivili (E), Thane 421204

Phone : 0251-2870260 Mobile : +91-9594079078 Email : info@durveshrasayan.com Website : www.durveshrasayan.com

S.B.R - 60 **Bonding Compound**

Durvexture – S.B.R - 60 is a Carboxylated Styrene-Butadiene Latex used for modification of hydraulic binders. The dispersion is free from plasticizers and film forming aids. It is manufactured by employing state-of-the-art emulsion polymerization technology ensuring product consistency.

Product Specifications

Properties	Specifications
Appearance	Milky white pourable liquid
Emulsifying System	Synthetic anionic and nonionic
Total Solids (%)	40 ± 1 or as per requirement
pH at 25°C	9.0 ± 0.5
Brookfield Viscosity cps SP.1.60 RPM at 25°C	150 max
Surface Tension (Dynes/cm) at 25°C	40 ± 5
Specific Gravity	1.015 ± 0.005
Dilutability in water	Dilutable in any proportion

Advantages

- High resistance to alkaline hydrolysis
- Provides excellent water impermeability
- Excellent workability at reduced water/ cement ratio
- Improved bonding and adhesion to substrate
- Longer pot life for polymer-cement mix
- Provides flexible cementitious coatings.

Packing

1, 5, 20, 50 & 100 litre

Shelf Life & Storage

The carboys should be stored between 5°C - 40°C and avoid exposure to sunlight.



URS is a member of Registrar of Standards (Holdings) Ltd.

Durvesh Rasayan Pvt Ltd
W-60, Phase II, MIDC,
Dombivili (E), Thane, 421204
Email : info@durveshrasayan.com
Contact : +91-9594079078

Note - The information included on this technical datasheet is the sole property of Durvesh Rasayan Pvt Ltd. The authorised disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit